



Head of Laboratory G. Briggs C. Text ATI

Client: Edmund Bell & Co Ltd
John Boyd Dunlop Drive
Unit E1A
Kingsway Business Park
Kingsway
Rochdale
OL164NG

Entry No: 47058

Date received: 26/05/2011

Client's Description: Fabric Ref 6904/78

TEST REPORT

Test Required: Flammability BS 5867-2 : Type C

Pre-treatment: Tests were made both before and after 50 washes in accordance with BS EN ISO 15028:1997 standard wash procedure (Type A) at 75 Degrees C followed by line and press drying.

Conditioning: A minimum of 24 hours at 65 +/- 5% Relative Humidity, 20 +/- 2°C

Method of Test: BS EN ISO 15025 : 2002 Procedure A (surface ignition)

Date of Test: 02/06/2011 & 07/06/2011

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

Flame application times 5, 15, 20 and 30 seconds using propane gas

As Received

No part of any hole or the lowest boundary of any flame reached the upper edge or either vertical edge on any specimen. There was no separation of flaming debris from any specimen.

After Washing

No part of any hole or the lowest boundary of any flame reached the upper edge or either vertical edge on any specimen. There was no separation of flaming debris from any specimen.

Comments

On the basis of the tests carried out this sample of fabric meets the Type C requirements of BS 5867-2 : 2008.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



G Briggs
Head of Laboratory
8th June 2011

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

